



COLOUR-FIL PU-8000

POLYURETHANE PAINT



COLOUR-FIL PU-8000 Polyurethane Paint is a premium quality, single stage, two component, Low VOC topcoat system. **PU-8000** has been formulated with premium ingredients to provide you with the ultimate in performance. This easy to use topcoat system offers exceptional application properties, coverage, film build and leaves behind a long-lasting, durable, high gloss, finish everytime! **PU-8000** can be used over all properly prepared OEM finishes and fully cured finishes. From spot panel repairs to overall refinishing, or as a fleet finish **PU-8000** will provide you with the finish you expect from a polyurethane system. It covers quickly, which means you use less material. **PU-8000** will increase productivity in your facility while reducing your labour and topcoat costs ... making it a very economical system. You have a choice of three Hardeners from fast to slow dry **H-8001**, **H-8002**, **H-8003**, and three Reducers **R-121**, **R-122**, **R-123** to meet your speed of dry requirements. Select the appropriate hardener and reducer to extract the optimum performance from the **PU-8000** Low VOC Polyurethane system.

Mix Ratio: 4 : 1 : 10%

Required Catalyst:
H-8001/H-8002/H-8003
COLOUR-FIL HARDENER

Reducer, Optional:
R-121/R-122/R-123



Refer to Product Data Sheet (PDS) PU-8000 for more information

Part No.	Description	Size	Units/Case
PU-8000	COLOUR-FIL Polyurethane Paint	3.78 L/1 US Gallon	4
H-8001	COLOUR-FIL Fast Hardener	946 mls/1 US Quart	6
H-8002	COLOUR-FIL Medium Hardener	946 mls/1 US Quart	6
H-8003	COLOUR-FIL Slow Hardener	946 mls/1 US Quart	6
R-121	FAST-FIL Fast Reducer	3.78 L/1 US Gallon	2
R-121.5	FAST-FIL Fast Reducer	18.9 L/5 US Gallons	Ea.
R-122	MEDIUM-FIL Medium Reducer	3.78 L/1 US Gallon	2
R-122.5	MEDIUM-FIL Medium Reducer	18.9 L/5 US Gallons	Ea.
R-123	SLOW-FIL Slow Reducer	3.78 L/1 US Gallon	2
R-123.5	SLOW-FIL Slow Reducer	18.9 L/1 US Gallon	Ea.

FEATURES

- Rich, High Gloss Finish
- Low V.O.C.
- Excellent Flow Out
- Excellent Coverage
- Excellent Hiding
- Excellent Flexibility
- Excellent Durability
- Excellent Chemical Resistance

COLOUR-FIL PU-8000

POLYURETHANE PAINT

COLOUR-FIL PU-8000 is a premium quality, Low VOC two component polyurethane topcoat system which will provide you with the ultimate in performance. **PU-8000** is for your day-to-day repairs, from spot panel repairs to overall refinishing, or as a fleet finish, air dry or force dry. This easy to use single stage system offers exceptional application properties, coverage, film build and leaves behind a durable, long-lasting, high gloss finish everytime! **PU-8000** can be applied over properly prepared OEM finishes and fully cured finishes. **PU-800** gets the job done fast as a result of its' excellent hiding properties. **PU-8000** covers quickly, which means you use less material. This system will increase productivity in your facility while reducing your labour and topcoat costs ... making it a very economical system to use.

PACKAGING: **3.78 L / 1 US GALLON PER CAN 4 CANS PER CASE**
 18.9 L / 5 US GALLONS PER PAIL

MATERIALS:	POLYURETHANE PAINT	PU-8000 COLOUR-FIL POLYURETHANE PAINT
	HARDENER	H-8001 COLOUR-FIL FAST HARDENER or H-8002 COLOUR-FIL MEDIUM HARDENER or H-8003 COLOUR-FIL SLOW HARDENER
	REDUCER	R-121 FAST-FIL FAST REDUCER or R-122 MEDIUM-FIL MEDIUM REDUCER or R-123 SLOW-FIL SLOW REDUCER

SURFACE PREPARATION:




Prepare a clean surface free of dirt, oil, wax, rust, and other contaminants. Properly prepare and clean all surfaces to be refinished consistent with good painting practices. It is recommended to dry sand the surface area with 400 grit sandpaper or finer, or wet sand with 800 grit sandpaper or finer.

PROTECTION:



Use only in a well ventilated area. Always wear the appropriate safety equipment. Consult with safety equipment supplier to ensure the proper safety equipment and protective clothing are being used.

MIX RATIO:



4 : 1 : 10%

4 Parts by Volume **PU-8000 COLOUR-FIL** Polyurethane Paint
1 Part by Volume **H-8001/H-8002/H-8003 COLOUR-FIL** Hardener
10% by Volume **R-121/R-122/R-123** Reducer




Stir mixture thoroughly and strain.
 Let mixture stand for 5 minutes before using.



PDS Form:
PU8000/LVCD AUS/1116_V01

POT LIFE:



2 ½ - 3 Hours @ 21° C / 70° F

SPRAY PRESSURE:



HVLP Spray Gun: 1.3 - 1.5 mm nozzle, 8 - 10 psi at ai cap (maximum)
Compliant Gravity Gun: 1.3 - 1.5 mm nozzle, 25 - 30 psi at the gun

* For best results, refer to spray gun manufacturer's recommendations for inlet air pressures


APPLICATION:



Using 25 - 30 psi at the gun, apply 2 - 3 wet coats of the mixture. Allow a 10 - 15 minute flash period between coats at 21°C/70°F.

* The flash time between coats will vary depending on the amount of material applied, temperature, and air flow.

FLASH TIME:



Allow a 10 - 15 minute @ 21°C / 70°F flash time between coats.

Note: Do NOT apply **PU-8000** paint over fresh or uncured coatings. Refinish surface must be completely cured prior to applying **PU-8000**.

DRY TIME:



Air Dry at 21° C / 70° F: Dust Free 20 - 25 Minutes * will vary per colour
Dry 2 - 3 Hours

* Dust Free and Dry times will vary according to amount of material applied, temperature, and air flow

Dry to Polish 12 Hours/Overnight

Before baking allow a 10 - 15 minute flash period at 21°C / 70°F after application of final coat. Bake for 30 - 45 minutes at 60°C / 140°F. Baking time will depend on amount of material applied. Let cool for 15 - 20 minutes before handling.

Force Dry at 60°C/140°F: Dry 20 - 30 Minutes
Dry to Polish 1 - 1 ½ Hours after cooling



PDS Form:
PU8000/LVCD AUS/1116_V01

**TECHNICAL
INFORMATION:**

Appearance:	Coloured Liquid
Weight Per Gallon:	3.59 kg - 4.58 kg / 7.85 lbs - 10.11 lbs Average
Specific Gravity:	0.941 - 1.187
% Solids By Weight:	40 - 61
Coats To Apply:	2 - 3
Recommended Dry Film:	3 - 4 mils
Dust Free Time:	20 - 25 Minutes @ 21° C / 70° F * will vary per colour
Pot Life:	2 ½ - 3 Hours @ 21° C / 70° F
Mix Ratio:	4 : 1: 10%
Required Catalyst:	COLOUR-FIL H-8001/H-8002/H-8003 Hardener
Required Reducer:	R-121/R-122/ or R-123 Reducer
Salt Spray:	150 Hours per ASTM B117

**SAFETY &
HANDLING:**

Important: For Industrial Use Only by trained professionals using proper safety equipment. Prior to using be sure to read and understand the warnings of this product and all products it may require, since the mixture will have the hazards of all its components. Observe all precautions for all components. Use only with adequate ventilation and wear the appropriate safety equipment. Refer to Material Safety Data Sheet (MSDS) for more and current information regarding this product and handling instructions.

The data contained in this publication are based on our current knowledge and experience. Many factors may affect processing, application, and performance of our products. The data and information contained herein does not imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. We shall not accept any liability for damages, skill of user, personal protective clothing and equipment, the materials used and processing conditions. The sellers and manufacturers liability on any claim, including negligence, loss, damage or injury, direct or other-wise resulting from manufacture, sale, resale, delivery, repair or use of any goods covered by or furnished shall not exceed the cost of replacing product. Any descriptions, data, proportions, weights, etc. given herein are for general information purposes only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. The latest version can be obtained from our website at www.durafil.ca or by contacting your sales representative or us directly.



DURAFIL
AUTO TECHNOLOGIES INC.

1360 Blundell Road
Mississauga, ON L4Y 1M5 Canada
Telephone: 905.896.7171 Toll Free: 877.505.7171